



Property	Tensile Strength	Elongation	Hardness	Density	Color	Application
Unit	Kg/cm <sup>2</sup>	%	ShoreA	Gr/cm <sup>3</sup>	---	---
Test Method	ASTM D 638	ASTM D 638	ASTM D 2240	ASTM D 792	---	---
H45	<b>210</b>	<b>260</b>	<b>88</b>		Gray	Telephon Insulation
PVC/D	<b>180</b>	<b>410</b>	<b>79</b>	<b>1.40</b>	Nat ural	Insulation
PVC/AS1	<b>225</b>	<b>325</b>	<b>86</b>	<b>1.40</b>	Nat ural	Insulation
H60T	<b>170</b>	<b>310</b>	<b>81</b>	<b>1.43</b>	Black	sheathing
H92A	<b>53</b>	<b>125</b>	<b>85</b>	<b>1.80</b>	Nat ural	Filler
H92AT	<b>63</b>	<b>140</b>	<b>85</b>	<b>1.79</b>	Nat ural	Filler
ST2	<b>165</b>	<b>320</b>	<b>79</b>	<b>1.45</b>	Black	sheathing
ST2-S	<b>145</b>	<b>385</b>	<b>78</b>	<b>1.43</b>	Black	sheathing
ST1-S	<b>175</b>	<b>335</b>	<b>80</b>	<b>1.45</b>	Black	sheathing
ST1-SAV	<b>180</b>	<b>310</b>	<b>85</b>	<b>1.48</b>	Gray	sheathing
ST5	<b>160</b>	<b>390</b>	<b>77</b>	<b>1.39</b>	Black	sheathing
ST5-G1	<b>170</b>	<b>390</b>	<b>77</b>	<b>1.40</b>	Gray	sheathing
H60 NS1	<b>170</b>	<b>285</b>	<b>83</b>	<b>1.46</b>	Black	Sheathing- Anti UV
YM5-S	<b>185</b>	<b>380</b>	<b>85</b>	<b>1.45</b>	Red	sheathing
GP0407	<b>135</b>	<b>405</b>	<b>74</b>	<b>1.39</b>	Black	High Temperature
C40GH	<b>185</b>	<b>430</b>	<b>77</b>	<b>1.36</b>	Black	Oil Resistant Insulation
GA0907-1	<b>250</b>	<b>350</b>	<b>87</b>	<b>1.29</b>	Nat ural	Insulation