



Laboratory & QC Department
Plasticized PVC Data Sheet

Property	Tensile Strength	Elongation	Hardness	Density	Appearance	Application
Unit	Kg/cm ²	%	ShoreA	Gr/cm ³	--	--
Test Method	ASTM D 638	ASTM D 638	ASTM D 2240	ASTM D 792	--	--
GM0840	105	360	71	1.30	Yellow	Boot soling
102	111	510	60	1.17	Natural Color	General Grade
108	170	440	71	1.20	Transparent	Soling
110	215	410	79	1.23	Transparent	Soling
10166	140	470	66	1.20	Transparent	Soling
10129	235	370	86	1.24	Natural Color	General Grade
GK0740	95	300	68	1.24	Yellow	Sport Shoe
10153-S1	225	335	87	1.29	Gray	Automotive Industry
10153-S4	205	360	85	1.28	Gray	Automotive Industry
10153-N	215	380	87	1.30	Natural	Automotive Industry
10157	195	475	76	1.22	Natural	Water Stop
Gk0407-1	205	440	79	1.25	Black	Sheathing
Gk0407-2	280	380	87	1.30	Black	Sheathing

Granule can be produced in accordance with your specification , other standards ,
analyzing your sample & price .

The colors can be changed as your request .